








**METHOD FOR PROCESSING A CONTINUOUSLY CAST METAL SLAB OR STRIP,  
AND PLATE OR STRIP PRODUCED IN THIS WAY**

**Patent number:** WO03018223  
**Publication date:** 2003-03-06  
**Inventor:** VAN DER WINDEN MENNO RUTGER (NL)  
**Applicant:** CORUS TECHNOLOGY BV (NL); VAN DER WINDEN  
MENNO RUTGER (NL)  
**Classification:**  
**- International:** B21B1/46  
**- european:** B21B1/22; B21B1/46; C21D8/02D2; C21D8/02D6;  
C22F1/04; C22F1/06; C22F1/08; C22F1/18B  
**Application number:** WO2002NL00547 20020816  
**Priority number(s):** NL20011018817 20010824

**Also published as:**

 WO03018223 (A1)  
 EP1420896 (A1)  
 EP1420896 (A1)  
 US2005000678 (A1)  
 CA2458270 (A1)  
more >>

**Cited documents:**

 US5665180  
 US5894879  
 US4238248  
 JP7333437  
 JP5318045  
more >>

**Report a data error here**

**Abstract of WO03018223**

The invention relates to a method for processing a continuously cast metal slab or strip, in which the slab or strip is passed between a set of rotating rolls of a rolling mill stand in order to roll the slab or strip. According to the invention, the rolls of the rolling mill stand have different peripheral velocities, and the difference in peripheral velocity is at least 5% and at most 100%, and the thickness of the slab or strip is reduced by at most 15% for each pass. The invention also relates to metal plate or strip produced using this method.

Data supplied from the [esp@cenet](mailto:esp@cenet) database - Worldwide

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
6 March 2003 (06.03.2003)

PCT

(10) International Publication Number  
**WO 03/018223 A1**

(51) International Patent Classification<sup>7</sup>: **B21B 1/46**

(21) International Application Number: PCT/NL02/00547

(22) International Filing Date: 16 August 2002 (16.08.2002)

(25) Filing Language: Dutch

(26) Publication Language: English

(30) Priority Data:  
1018817 24 August 2001 (24.08.2001) NL

(71) Applicant (*for all designated States except US*): **CORUS TECHNOLOGY BV** [NL/NL]; P.O. Box 10000, NL-1970 CA IJmuiden (NL).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): **VAN DER WINDEN, Menno, Rutger** [NL/NL]; Witte Singel 93A, NL-2311 BR Leiden (NL).

(74) Agent: **KRUIT, Jan**; Corus Technolgo BV, P.O. Box 10000, NL-1970 CA IJmuiden (NL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: METHOD FOR PROCESSING A CONTINUOUSLY CAST METAL SLAB OR STRIP, AND PLATE OR STRIP PRODUCED IN THIS WAY

(57) Abstract: The invention relates to a method for processing a continuously cast metal slab or strip, in which the slab or strip is passed between a set of rotating rolls of a rolling mill stand in order to roll the slab or strip. According to the invention, the rolls of the rolling mill stand have different peripheral velocities, and the difference in peripheral velocity is at least 5% and at most 100%, and the thickness of the slab or strip is reduced by at most 15% for each pass. The invention also relates to metal plate or strip produced using this method.



**WO 03/018223 A1**

**METHOD FOR PROCESSING A CONTINUOUSLY CAST METAL SLAB OR STRIP, AND PLATE OR STRIP PRODUCED IN THIS WAY**

The invention relates to a method for processing a  
5 continuously cast slab or strip, in which the slab or strip  
is passed between a set of rotating rolls of a rolling mill  
stand in order to roll the slab or strip.

Rolling is a very standard processing operation for  
10 imparting desired dimensions and properties to metals. For  
example, rolling results in an improvement to the  
microstructure as a result of grain refinement taking place  
under the influence of the rolling.

15 If thin plate or strip is to be produced from a thick slab  
of, for example, 30 cm or more, the production of thin  
plate or strip is a very laborious process, since rolling  
has to be repeated a very large number of times. Therefore,  
other casting techniques have been developed in order to  
20 obtain a thin slab or a strip directly. In order still to  
produce sufficient material, these processes are carried  
out continuously.

For the continuous casting of aluminum, in principle three  
25 methods can be distinguished which are currently in use.  
The first method uses one cooled roll on which a thin layer  
of molten aluminum is cooled until it solidifies. The strip  
obtained in this way has a thickness of approximately 1 mm.  
For technical reasons, this thickness cannot be much  
30 greater. The second method uses two cooled rolls between  
which molten aluminum is passed in order to solidify into a  
strip. The improved cooling means that this method usually  
produce a thickness of between 6 and 10 mm; the minimum  
thickness which can currently be achieved is approximately  
35 1 mm. Depending, inter alia, on the thickness, the strip  
which is formed will be cut into slabs or coiled. In the  
third method, the molten aluminum is guided onto a conveyer  
belt, on which it solidifies, or passed between two  
conveyer belts in order to solidify. On account of the

longer solidification path, more heat can be dissipated and it is possible to produce a thicker solidified strip. The thickness is usually approximately 20 mm. The thick strip formed in this way can then be cut in slabs or coiled. In all three methods, it is also possible for the strip to be rolled in one or more rolling mill stands immediately after the continuous casting and then to be coiled.

The above three methods or also other methods can be used for the continuous casting of other metals, and if appropriate it is also possible to produce a thicker strip.

These methods and methods derived from them are in the present context jointly referred to as "continuous casting", and the product obtained thereby is referred to as "continuously cast slab or strip".

One drawback of these products is that the end product still largely has the cast microstructure, since the slabs and the strip have scarcely been rolled. Consequently, the mechanical properties of the end products are relatively poor, and consequently the use of the end products is relatively limited, for example as a foil and a starting material for fins of heat exchangers and the like.

It is an object of the invention to provide a method for processing a continuously cast metal slab or strip which allows the properties of the product produced thereby to be improved.

It is another object of the invention to provide a method for processing a continuously cast metal slab or strip with which it is possible to close up pores in the cast material.

Yet another object of the invention is to provide a method for processing a continuously cast metal slab or strip which results in grain refinement in the product which is thereby produced.

Yet another object of the invention is to provide a method for processing continuously cast metal by means of which the surface of the slab or strip is improved.

5

It is also an object of the invention to provide a metal plate or strip with improved mechanical properties which is preferably produced with the aid of this method.

10 According to a first aspect of the invention, one or more of these objects are achieved by a method for processing a continuously cast slab or strip, in which the slab or strip is passed between a set of rotating rolls of a rolling mill stand in order to roll the slab or strip, in which method  
15 the rolls of the rolling mill stand have different peripheral velocities, and the difference in peripheral velocity is at least 5% and at most 100%, and in which method the thickness of the slab or strip is reduced by at most 15% for each pass.

20

As a result of the rolls being provided with a different peripheral velocity, shearing occurs in the slab or strip and has been found to occur throughout the entire thickness of the slab or strip. It has been found that this requires  
25 a velocity difference of at least 5%. The shearing leads to pores in the continuously cast material being closed up to a considerable extent. This does not require a major change in thickness, but rather a change in thickness of at most 15% can suffice. This is advantageous in a continuously  
30 cast metal slab or strip, which in many cases is cast with a low thickness, because the thickness is then substantially retained.

In addition, it is important that the rolling according to  
35 the invention can result in a grain refinement which occurs throughout the entire thickness of the rolled material, which is advantageous for the mechanical properties of the slab or strip. Inter alia, the strength of the material increases.

The shearing also breaks up the eutectic particles, which results in an improved toughness.

5 In addition, it is expected that the material will have an improved fatigue crack growth rate, since the grains will have a more or less knurled shape as a result of the shearing. This results in an improved toughness and a reduced susceptibility to damage.

10

It is also expected that the processing according to the invention will result in a rolled sheet with less spread.

15 It is also expected that the processing according to the invention will cause the surface layer of the material to be different than is the case with conventional rolling of the material. Ordinary rolling results in the formation of a layer comprising very fine-grained material. This layer is much thinner in the processing according to the  
20 invention. The expectation is that this will improve the corrosion resistance of the material. This may be favorable for the use of continuously cast aluminum plates and strip material for applications other than the current ones.

25 The thickness of the slab or strip is preferably reduced by at most 8% for each pass, and preferably by at most 5%. Since the shearing and therefore the grain refinement are brought about by the difference in peripheral velocity between the rolls, the reduction in thickness of the  
30 material is not necessary in order to obtain grain refinement. The reduction in thickness is required primarily in order to enable the rolls to grip the material. This only requires a slight change in thickness, which is advantageous in the case of thin continuously cast  
35 aluminum slabs and strip material. The smaller the reduction, the thicker the slab or strip remains after each pass. The possible applications of continuously cast aluminum slabs and strip material increase as a result.

The difference in peripheral velocity is preferably at least 20%, more preferably at least 50%. As the difference in peripheral velocity of the rolls is larger, the shearing will be higher. As a result, the grain refinement becomes stronger and the mechanical properties increase.

According to an advantageous embodiment, the rolling mill is designed in such a manner that the rolls have different diameters. This makes it possible to obtain the desired difference in peripheral velocity.

According to another advantageous embodiment, the rolls have a different rotational speed. This too makes it possible to obtain the desired difference in rotational speed.

It is also possible for these latter two measures to be combined in order to obtain the desired difference in rotational speed.

The rolling is preferably carried out at an elevated temperature. This makes the rolling run more smoothly. The rolling is preferably carried out at a temperature between 300 and 550°C, since in this temperature range good deformation on the continuously cast aluminum slabs and strip is possible. More preferably, the rolling is carried out at a temperature between 425 and 475°C. The deformation of aluminum is easiest at approximately 450°C.

According to an advantageous embodiment of the method, the slab is introduced between the rolls at an angle of between 5 and 45° with respect to the perpendicular to the plane through the center axes of the rolls. Introducing the slab between the rolls at an angle makes it easier for the rolls to grip the slab, with the result that the change in thickness can be kept as low as possible. The slab is preferably fed in at an angle of between 15 and 25°, since the grip of the rolls is best in that case.

The starting point is preferably a slab or strip with a thickness of at most 70 mm, more preferably at most 25 mm. Standard rolling involves rolling to a thickness of approximately one millimeter or thinner in order to obtain better mechanical properties. With the aid of the method according to the invention, better mechanical properties can be imparted to the slab or strip, with the result that thinner material can be used for same application. Since the method according to the invention can be used to impart better properties to the relatively thin continuously cast metal, it is to be expected that thicker continuously cast plate and strip material, now with better mechanical properties, will also find industrial applications.

For this purpose, after the rolling has been carried out for the first time, the processing operating is preferably repeated one or more times. For example, sufficiently good grain refinement is obtained by carrying out the processing operating according to the invention three times. However, the number of times that the processing operation has to be carried out depends on the thickness of the continuously cast material, the difference in peripheral velocity of the rolls and the desired grain refinement.

By carrying out the processing operation according to the invention a large number of times and subjecting the material to an annealing treatment in between these operations if necessary, it is possible to obtain an ultrafine grain structure. The processing operation can be repeated sufficiently often for the material to become superplastic. Superplastic material has extremely small grains and as a result under certain conditions can stretch almost infinitely without cracking. This is a highly advantageous property for the deformation of metal, for example deep-drawing of a blank. Obviously, when the processing operation according to the invention is repeated a number of times, the material does become thinner, and it is therefore desirable to start from a continuously cast metal, such as aluminum, with the maximum possible



thickness.

If the processing operation according to the invention is repeated a number of times, according to an advantageous embodiment the slab, plate or strip can be passed through the rolling mill stand in opposite directions for each pass. The slab, plate or strip then changes direction after each rolling operation and is always passed through the same rolling mill stand. In this case, the rolls have to rotate in opposite directions for each pass.

According to another advantageous embodiment, the slab, plate or strip is successively passed through two or more rolling mill stands. This method is suitable primarily for strip material, which in this way can undergo the desired processing operation very quickly.

It is possible for the method according to the invention to be preceded or followed by a rolling operation which is carried out using a rolling mill in which the rolls have substantially identical peripheral velocities. In this way, by way of example, an accurately desired thickness or smoothness can be imparted to the product.

According to an advantageous embodiment, the metal slab is formed by two or more layers of metal, preferably two or more layers consisting of different alloys of a metal or different metals. In this way it is possible, for example, to produce laminated material, such as what is known as clad material for, for example, aluminum brazing sheet.

Another aspect of the invention provides a metal plate or strip produced using the above method, in which the metal is aluminum, steel, stainless steel, copper, magnesium or titanium or an alloy of one of these metals. These metals and their alloys are particularly suitable for production with the aid of the method according to the invention, since they are metals which are in widespread use in industry and for which it is very desirable to obtain

better mechanical properties if they are produced by continuous casting.

5 A continuously cast metal plate preferably has a thickness of between 5 and 60 mm, more preferably between 5 and 20 mm. This thickness is obviously dependent on the thickness with which the metal can be continuously cast. Therefore, the processing operation according to the invention makes it possible to produce relatively thick plates with good  
10 mechanical properties even from relatively thin continuously cast material.

The plate preferably consists of an aluminum alloy from the AA 1xxx or the AA 3xxx series, preferably AA 1050 or AA  
15 1200, or AA 3103.

A continuously cast metal strip preferably has a thickness of at most 7 mm, more preferably at most 2 mm. By means of the processing operation according to the invention, it is  
20 possible to obtain relatively thick strip material with good mechanical properties, although it is also possible, of course, to provide the strip with a standard thickness or even to make it thinner, since the mechanical properties are improved.

25 The metal strip is, for example, a strip consisting of an aluminum alloy from the AA 5xxx series, preferably AA 5182. This material can be used as auto body sheet as a result of the processing operation according to the invention.

30 The invention also relates to an improved metal plate or strip which has been produced by continuous casting, preferably with the aid of the method according to the first aspect of the invention, in which the pores in the  
35 core of the plate or strip have a maximum dimension of less than 20  $\mu\text{m}$ , preferably less than 10  $\mu\text{m}$ . As a result of the continuous casting, continuously cast plate and strip material always has pores which are significantly larger than 20  $\mu\text{m}$ . The standard rolling operations can only close

up these pores in the core to a slight extent or cannot do so at all. The rolling operation according to the invention makes it possible to provide continuously cast plate and strip material having pores which are much smaller.

5

The invention also relates to an improved metal plate or strip which is produced by continuous casting, preferably with the aid of the method according to the first aspect of the invention, in which the unrecrystallized metal plate or strip, in the core of the plate or billet, has a deformed grain structure, the grain having a mean length which is 2 to 20 times greater than their thickness, preferably a length which is 5 to 20 times greater than their thickness. Since with conventional rolling continuously cast metal is only subject to slight deformation in the core, the metal grains in the core are scarcely deformed. The rolling treatment according to the invention makes it possible to provide continuously cast plate and strip material with highly deformed grains. As a result, a very fine grain structure will be formed during recrystallization.

The invention also relates to an improved metal plate or strip which is produced by continuous casting, preferably with the aid of the method according to the first aspect of the invention, in which the metal plate or strip, after recrystallization, has a substantially homogenous degree of recrystallization over its entire thickness. The fact that the grains have all been subjected to shearing as a result of the rolling operation according to the invention, including those in the core, means that the continuously cast plate and strip material will recrystallize over the entire thickness.

The metal plate or strip with this size of pores, deformed grain structure or this level of recrystallization is preferably made from aluminum, steel, stainless steel, copper, magnesium or titanium or an alloy thereof, since these metals are readily capable of industrial application.

**CLAIMS**

1. A method for processing a continuously cast slab or strip, in which the slab or strip is passed between a set  
5 of rotating rolls of a rolling mill stand in order to roll the slab or strip, characterized in that the rolls of the rolling mill stand have different peripheral velocities, and the difference in peripheral velocity is at least 5% and at most 100%, and in that the thickness of the slab or  
10 strip is reduced by at most 15% for each pass.
2. The method as claimed in claim 1, in which the thickness of the slab or strip is reduced by at most 8% each pass, and preferably at most 5%.
- 15 3. The method as claimed in claim 1 or 2, in which the difference in peripheral velocity is at least 20% and preferably at least 50%.
- 20 4. The method as claimed in one of the preceding claims, in which the rolling mill is designed in such a manner that the rolls have different diameters.
5. The method as claimed in one of the preceding claims,  
25 in which the rolls have different rotational speeds.
6. The method as claimed in one of the preceding claims, in which the rolling is carried out at an elevated temperature, for aluminum preferably at a temperature  
30 between 300 and 550°C, and more preferably at a temperature between 425 and 475°C.
7. The method as claimed in one of the preceding claims, in which the slab is introduced between the rolls at an  
35 angle of between 5 and 45° with respect to the perpendicular to the plane through the center axes of the rolls, preferably at an angle between between 15 and 25°.
8. The method as claimed in one of the preceding claims,

in which the starting point is a slab or strip with a thickness of at most 70 mm, preferably at most 25 mm.

9. The method as claimed in one of the preceding claims,  
5 in which the processing operation is repeated one or more times after the rolling has been carried out for the first time.

10. The method as claimed in claim 9, in which the slab,  
10 plate or strip is passed through the rolling mill stand in opposite directions for each pass.

11. The method as claimed in claim 9, in which the slab,  
plate or strip is successively passed through two or more  
15 rolling mill stands.

12. The method as claimed in one of the preceding claims,  
in which the processing operation as described in one of  
claims 1 - 11 is preceded or followed by a rolling  
20 operation which is carried out using a rolling mill in which the rolls have substantially identical peripheral velocities.

13. Method according to one of the preceding claims, in  
25 which the metal slab is formed by two or more layers of metal, preferably two or more layers consisting of different alloys of a metal or different metals.

14. Metal plate or strip produced using the method as  
30 claimed in one of claims 1 - 13, in which the metal is aluminum, steel, stainless steel, copper, magnesium or titanium or an alloy thereof.

15. The metal plate as claimed in claim 14, which has a  
35 thickness of between 5 and 60 mm, preferably between 5 and 20 mm.

16. The metal plate as claimed in claim 15, which plate consists of an aluminum alloy from the AA 1xxx or AA 3xxx

series, preferably AA 1050 or AA 1200, or AA 3103.

17. The metal strip as claimed in claim 14, which has a thickness of at most 7 mm, preferably at most 2 mm.

5

18. The metal strip as claimed in claim 17, which consists of an aluminum alloy from the AA 5xxx series, preferably AA 5182.

10 19. The use of aluminum strip as claimed in claim 18 in a vehicle, for example as a structural part in the interior of the vehicle.

15 20. A metal plate or strip produced by continuous casting, preferably with the aid of the method as claimed in one of claims 1 - 13, in which the pores in the core of the plate or strip have a maximum dimension of less than 20  $\mu\text{m}$ , preferable less than 10  $\mu\text{m}$ .

20 21. A metal plate or strip produced by continuous casting, preferably with the aid of the method as claimed in one of claims 1 - 13, in which the unrecrystallized metal plate or strip, in the core of the plate or billet, has a deformed grain structure, the grain having a mean length which is 2  
25 to 20 times greater than their thickness, preferably a length which is 5 to 20 times greater than their thickness.

30 22. A metal plate or strip produced by continuous casting, preferably with the aid of the method as claimed in one of claims 1 - 13, in which the metal plate or strip, after recrystallization, has a substantially homogenous degree of recrystallization over its entire thickness.

35 23. The metal plate or strip as claimed in claim 20, 21 or 22, in which the metal is aluminum, steel, stainless steel, copper, magnesium or titanium or an alloy thereof.

## INTERNATIONAL SEARCH REPORT

PCT/NL 02/00547

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 B21B1/46

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 B21B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 665 180 A (SEETHARAMAN VENKAT K ET AL) 9 September 1997 (1997-09-09) claim 1E	1-23
A	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 04, 30 April 1996 (1996-04-30) & JP 07 333437 A (FUJI PHOTO FILM CO LTD), 22 December 1995 (1995-12-22) abstract	1-23
A	PATENT ABSTRACTS OF JAPAN vol. 018, no. 130 (M-1570), 3 March 1994 (1994-03-03) & JP 05 318045 A (MITSUBISHI MATERIALS CORP), 3 December 1993 (1993-12-03) abstract	1-23
	--- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the International filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the International filing date but later than the priority date claimed

- \*T\* later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*G\* document member of the same patent family

Date of the actual completion of the international search

9 January 2003

Date of mailing of the International search report

16/01/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

De Gussem, J

# INTERNATIONAL SEARCH REPORT

Application No.  
PCT/NL 02/00547

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 010, no. 214 (C-362), 25 July 1986 (1986-07-25) & JP 61 052317 A (KOBE STEEL LTD), 15 March 1986 (1986-03-15) abstract ----	1-23
A	PATENT ABSTRACTS OF JAPAN vol. 005, no. 172 (M-095), 31 October 1981 (1981-10-31) & JP 56 099004 A (NIPPON STEEL CORP), 10 August 1981 (1981-08-10) abstract ----	1-23
A	PATENT ABSTRACTS OF JAPAN vol. 004, no. 139 (M-034), 30 September 1980 (1980-09-30) & JP 55 094707 A (KAWASAKI STEEL CORP), 18 July 1980 (1980-07-18) abstract ----	1-23
A	PATENT ABSTRACTS OF JAPAN vol. 004, no. 088 (M-017), 24 June 1980 (1980-06-24) & JP 55 045507 A (NIPPON STEEL CORP), 31 March 1980 (1980-03-31) abstract ----	1-23
A	PATENT ABSTRACTS OF JAPAN vol. 004, no. 068 (M-012), 21 May 1980 (1980-05-21) & JP 55 033851 A (KAWASAKI STEEL CORP), 10 March 1980 (1980-03-10) abstract ----	1-23
A	US 5 894 879 A (WESTERMAN EDWIN JAMES ET AL) 20 April 1999 (1999-04-20) claim 1 ----	1-23
A	US 4 238 248 A (BOLLIGER MARTIN ET AL) 9 December 1980 (1980-12-09) claim 1 ----	1-23
A	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 14, 22 December 1999 (1999-12-22) & JP 11 254093 A (FUJI PHOTO FILM CO LTD), 21 September 1999 (1999-09-21) abstract -----	1-23



## INTERNATIONAL SEARCH REPORT

PCT/NL 02/00547

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5665180	A	09-09-1997	NONE
JP 07333437	A	22-12-1995	NONE
JP 05318045	A	03-12-1993	NONE
JP 61052317	A	15-03-1986	NONE
JP 56099004	A	10-08-1981	NONE
JP 55094707	A	18-07-1980	JP 1238142 C 31-10-1984 JP 59010843 B 12-03-1984
JP 55045507	A	31-03-1980	JP 1388082 C 14-07-1987 JP 59013281 B 28-03-1984
JP 55033851	A	10-03-1980	NONE
US 5894879	A	20-04-1999	US 5655593 A 12-08-1997 AU 722391 B2 03-08-2000 AU 7362596 A 09-04-1997 BR 9611416 A 23-02-1999 CA 2232436 A1 27-03-1997 CN 1200771 A ,B 02-12-1998 EP 0851943 A1 08-07-1998 JP 11511389 T 05-10-1999 WO 9711205 A1 27-03-1997
US 4238248	A	09-12-1980	AU 522546 B2 10-06-1982 AU 4931979 A 07-02-1980 BE 878056 A1 03-12-1979 CA 1171235 A1 24-07-1984 CA 1193524 A2 17-09-1985 CH 641495 A5 29-02-1984 CH 641496 A5 29-02-1984 DE 2901028 A1 14-02-1980 DE 2901029 A1 14-02-1980 ES 482916 A1 16-05-1980 FR 2442896 A1 27-06-1980 FR 2440997 A1 06-06-1980 GB 2027621 A ,B 27-02-1980 IN 151586 A1 28-05-1983 IT 1122428 B 23-04-1986 JP 55027497 A 27-02-1980 NL 7905903 A 06-02-1980 NO 792542 A ,B, 05-02-1980 SE 447395 B 10-11-1986 SE 7906556 A 05-02-1980 ZA 7903979 A 27-08-1980
JP 11254093	A	21-09-1999	NONE